

High Range Water Reducing & Retarding Admixture

Uses

- To produce pumpable concrete
- To increase workability without extra water
- To improve cohesion, minimising segregation and give better finish.
- Chloride free, safe for use in prestressed and reinforced concrete
- Can be used with concrete containing microsilica and other cement replacements.

Advantages

- **Improved workability** - Easier , quicker placing and compaction.
- **Increased strength** - Provides high early strength if water reduction is taken advantage of.
- **Increased quality** - Denser, close textured concrete with reduced porosity and hence enhanced durability.
- **Higher cohesion** - Risk of segregation and bleeding minimised; thus aids pumping of concrete

Standards compliance

Conplast SP430T1 complies with IS:9103:1999 and BS:5075 Part 3 - 1985, and ASTM-C-494 / C494M - 99a Type 'G' as a high range water reducing admixture.

Description

Conplast SP430T1 is based on Sulphonated Napthalene Polymers and is supplied as a brown liquid instantly dispersible in water.

Conplast SP430T1 has been specially formulated to give high water reductions upto 25% without loss of workability or to produce high quality concrete of reduced permeability.

Properties

Specific gravity	1.25 to 1.280 at 27°C
Chloride content	Nil to BS5075
Air entrainment	Approx. 1.5% additional air is entrained

Compatibility : Can be used with all types of cements except high alumina cement. Conplast SP430T1 is compatible with other Conplast admixtures when added separately to the mix. Site trials should be carried out to optimise dosages.

Workability : Can be used to produce flowing concrete that requires no compaction. Some minor adjustments may be required to produce high workable mix without segregation.

Cohesion : Cohesion is improved due to dispersion of cement particles thus minimising segregation and improving surface finish.

Compressive strength : Early strength is increased upto 40 to 50% if water reduction is taken advantage of. Generally, there is improvement in strength upto 20% depending upon W/C ratio and other mix parameters.

Durability : Reduction in W/C ratio enables increase in density and impermeability thus enhancing durability of concrete.

Application instructions

Dosage

The optimum dosage is best determined by site trials with the concrete mix which enables the effects of workability, strength gain or cement reduction to be measured. Site trials with Conplast SP430T1 should always be compared with mix containing no admixture. As a guide, the rate of addition is generally in the range of 0.6 - 1.5 % by weight of cement.

Over dosing

An over dose above the recommended level of admixture may result in high workability, air entrainment and retardation of setting time depending on the ambient temperature of cure. As such, more than the recommended dosage may be used if necessary by ascertaining the performance in the lab trials only before using in actual site conditions.

Dispensing

The correct quantity of Conplast SP430T1 should be used by means of a dispenser. The measured quantity of Conplast SP430T1 should be added along with the gauging water incase of batching plants. Alternatively, correct dosage should be used with about 20% of the total water in the last phase after the mix has been prewetted.

Mix design

Fosroc has an advisory service on Concrete Mix Design and can be contacted if assistance is required.

Conplast® SP430T1

Estimating

Packing

Conplast SP430T1 is supplied in 5,20 and 200 litre drums.

Storage

Conplast SP430T1 has a minimum shelf life of 12 months when stored under normal temperatures. It should be protected from extreme temperatures and preferably stored in shade.

Precautions

Health & Safety

Conplast SP430T1 is non-toxic. Any splashes on the skin should be washed immediately with water. Splashes to the eyes should be washed immediately with water and medical advice should be sought.

Fire

Conplast SP430T1 is non flammable.

® Denotes the trademark of Fosroc International Limited

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone

+91 80-22240018/120

fax

+91 80-22233474

e-mail

india@fosroc.com

Regional Offices



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

111/3, Hafeeza Chamber II Floor,
K H Road, PBN0. 2744, Bangalore 560027

www.fosroc.com

Bangalore

Shankar House, IV Floor
1 & 18, RMV Extension
Bangalore 560 080
Ph:080-2361 3161/2361 2004
Fax : 080-2361 7454
email: Bangalore@fosroc.com

Mumbai

208/209, Persepolis
Sector 17, Vashi
Navi Mumbai 400 703
Ph:022-2789 6412/14
Fax: 022 - 2789 6413
email:Mumbai@fosroc.com

Delhi

First floor,1/2 East Patel Nagar
Opp: Vivek Cinema, Main Patel Rd
New Delhi 110 008
Ph:011-25884903/4
Fax: 011- 25884422
email:Delhi@fosroc.com

Kolkata

P-569, Lake Terrace Extn.
First Floor
Kolkata 700 029
Ph: 033 24650917 / 55343188
Fax: 033-24650891
email:Kolkata@fosroc.com

- Ahmedabad : (079) 26762799 ● Ankleshwar : (02646) 220704/224687 ● Bhubaneshwar : (0674) 2546415 ● Chennai (044) 24899949/24853383
- Chandigarh : (0172) 2639360 ● Cochin : (0484) 2356668 ● Coimbatore : (0422) 2472966 ● Goa : (0832) 2542465 ● Guwahati (0361) 2548793
- Hyderabad : (040) 27662324/27662425 ● Hubli (0836) 09343402597 ● Indore : (0731) 504339/5061477 ● Jaipur : (0141) 2235349
- Jamshedpur : (0657) 2223848 ● Lucknow : (0522) 2239044 ● Nagercoil 09842134873 ● Visakhapatnam : (0891) 2564850 / 2707607