



Conplast® SP432MS(P)

High Performance admixture for OPC, Slag cement and Microsilica concrete

Uses

- To provide increased ultimate strength gain by significantly reducing water demand in a concrete mix
- Suitable for Precast & High Performance Concrete M40 above
- Specifically developed for use with OPC, slag cement and microsilica concrete
- To significantly improve the workability and retention of site mixed concrete without increasing water demand
- To provide improved durability by increasing ultimate strengths and reducing concrete permeability

Advantages

- Makes possible major reductions in water cement ratio which allows the production of high strength concrete without excessive cement contents.
- Increased workability levels are maintained for longer than with ordinary sulphonated melamine and naphthalene admixtures
- Improved cohesion and particle dispersion minimises segregation and bleeding and improves pumpability
- Chloride free, safe for use in prestressed and reinforced concrete.

Standards compliance

Conplast SP432MS(P) complies with IS9103:1999, BS 5075 Part 3 and with ASTM C494 Type 'F' and Type 'G' admixture depending on dosage used.

Description

Conplast SP432MS(P) is a chloride free, superplasticising admixture based on selected sulphonated naphthalene polymers. It is supplied as a brown solution which instantly disperses in water.

Conplast SP432MS(P) disperses the fine particles in the concrete mix, enabling the water content of the concrete to perform more effectively. The very high levels of water reduction possible allow major increases in strength to be obtained.

Technical support

Fosroc provides a technical advisory service for on-site assistance and advice on mix design, admixture selection, evaluation trials and dispensing equipment.

Typical dosage

The optimum dosage of Conplast SP432MS(P) to meet specific requirements should always be determined by trial mixes using the materials and conditions that will be experienced in use.

For high strength, water reduced concrete the normal dosage range is from 0.6 - 2.0 litres/100kg of cementitious material, including PFA, GGBFS and microsilica.

Use at other dosages

Dosages outside the typical ranges quoted above can be used to meet particular requirements. Contact Fosroc for advice.

Properties

Appearance	Brown liquid
Chloride content	Nil to BS 5075
Air entrainment	Typically less than 1.5% additional air is entrained at normal dosages.
Alkali content	Typically less than 72.0g Na ₂ O equivalent per litre of admixture.

Instructions for use

Mix design

Where the main requirement is to improve strengths, initial trials should be made with normal concrete mix designs. The addition of the admixture will allow the removal of water from the mix whilst maintaining workability. After initial trials, minor modifications to the overall mix design may be made to optimise performance. When the main requirement is to provide high workability concrete, the mix design should be one suitable for use as a pump mix.

Compatibility

Conplast SP432MS(P) is compatible with other Fosroc admixtures used in the same concrete mix. All admixtures should be added to the concrete separately and must not be mixed together prior to addition. The resultant properties of concrete containing more than one admixture should be assessed by trial mixes.

Conplast[®] SP432MS(P)

Conplast SP432MS(P) is suitable for use with all types of ordinary portland cements and cement replacement materials such as PFA, GGBFS and microsilica.

Dispensing

The correct quantity of Conplast SP432MS(P) should be measured by means of a recommended dispenser. Normally, the admixture should then be added to the concrete with the mixing water to obtain the best results.

Effects of overdosing

An overdose of double the amount of Conplast SP432MS(P) will result in an increase in retardation as compared to that normally obtained. Provided that adequate curing is maintained, the ultimate strength of the concrete will not be impaired by increased retardation and will generally be increased. The effects of overdosing will be further increased if sulphate resisting cement or cement replacement materials are used.

Over dosage may also cause increased air entrainment, which will tend to reduce strength. The degree of this effect will depend on the particular mix design and overdose level.

Estimating

Packaging

Conplast SP432MS(P) is available in drum or bulk supply.

Storage

Conplast SP432MS(P) has a minimum shelf life of 12 months provided the temperature is kept within the range of 2°C to 50°C.

Freezing point : Approximately -2°C.

Precautions

Health & Safety instructions

Conplast SP432MS(P) is non hazardous. However it should not be swallowed or allowed to come into contact with skin and eyes. Suitable protective gloves and goggles should be worn. Splashes on the skin should be removed with water. In case of contact with eyes rinse immediately with plenty of water and seek medical advice. If swallowed, seek medical attention immediately - do not induce vomiting.

Fire

Conplast SP432MS(P) is water based and non flammable.

Cleaning and disposal

Spillages of Conplast SP432MS(P) should be absorbed onto sand, earth or vermiculite and transferred to suitable containers. Remnants should be hosed down with large quantities of water.

The disposal of excess or waste material should be carried out in accordance with local legislation under the guidance of the local waste regulatory authority.

® Denotes the trademark of Fosroc International Limited

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone

+91 80-22240018/120

fax

+91 80-22233474

e-mail

india@fosroc.com

Regional Offices



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

111/3, Hafeeza Chamber II Floor,
K H Road, PBNo. 2744, Bangalore 560027

www.fosroc.com

Bangalore

Shankar House, IV Floor
1 & 18, RMV Extension
Bangalore 560 080
Ph:080-2361 3161/2361 2004
Fax : 080-2361 7454
email: Bangalore@fosroc.com

Mumbai

208/209, Persepolis
Sector 17, Vashi
Navi Mumbai 400 703
Ph:022-2789 6412/14
Fax: 022 - 2789 6413
email:Mumbai@fosroc.com

Delhi

First floor, 1/2 East Patel Nagar
Opp: Vivek Cinema, Main Patel Rd
New Delhi 110 008
Ph:011-25884903/4
Fax: 011- 25884422
email:Delhi@fosroc.com

Kolkata

P-569, Lake Terrace Extn.
First Floor
Kolkata 700 029
Ph: 033 24650917 / 55343188
Fax: 033-24650891
email:Kolkata@fosroc.com

- Ahmedabad : (079) 26762799 ● Ankleshwar : (02646) 220704/224687 ● Bhubaneshwar : (0674) 2546415 ● Chennai (044) 24899949/24853383
- Chandigarh : (0172) 2639360 ● Cochin : (0484) 2356668 ● Coimbatore : (0422) 2472966 ● Goa : (0832) 2542465 ● Guwahati (0361) 2548793
- Hyderabad : (040) 27662324/27662425 ● Hubli (0836) 09343402597 ● Indore : (0731) 504339/5061477 ● Jaipur : (0141) 2235349
- Jamshedpur : (0657) 2223848 ● Lucknow : (0522) 2239044 ● Nagercoil 09842134873 ● Visakhapatnam : (0891) 2564850 / 2707607

INDIA/2005/01-127/B

