



# Conbextra® WS60

## Rapid foaming and setting resin for stopping flow of water

### Uses

STOPS the flow of water when injected into cracks in concrete in the presence of moving water. Conbextra WS60 with Conbextra UR63 provides an effective system for crack sealing in wet conditions.

### Advantages

- **Seals against water:** Reacts and produces foam resistant to water
- **Rapid acting:** Rapid reaction to produce water stop in presence of flowing water
- **Reinjectable:** Can be reinjected with Conbextra UR 63 to produce a permanent seal.

### Description

Conbextra WS60 is a two part liquid polyurethane when mixed in the proportions supplied it reacts rapidly with water to form a foam barrier.

### Technical support

The company provides a technical advisory service supported by a team of specialists in the field

### Typical properties

<b>Specific gravity</b>	1.14 ± 0.06
<b>Density of foam</b>	0.025
<b>Viscosity at 20°C</b>	2 - 3 poise
<b>Pot life, in absence of water</b>	
<b>at 20°C</b>	6 - 8 hours
<b>at 30°C</b>	3 - 4 hours
<b>Reaction time with water</b>	5 to 30 seconds dependent upon temperature

### Application instructions

If water flow permits then the surfaces should be free from oil, grease and other contaminants. Conbextra WS60 can be applied using either injection plugs or adhesion packers (nipples) bonded to the surface with Nitomortar PE.

### Instructions for use of Nitomortar PE

#### Surface preparation

Nitomortar PE has to retain the injection system under pressure. Care must be taken to provide a clean and sound surface for bonding

1. Remove heavy deposits of grease and dirt by scrubbing with detergent solution and washing with plenty of clean water to ensure complete removal of the detergent. Dirt alone may be removed with wire brushes or similar mechanical means.
2. Remove deteriorated concrete, laitence and paint. The best treatment is grit blasting with sand, steel shot or a proprietary abrasive. Where grit blasting is impracticable, use rotary wire brushes.
3. Blow the cracks and treated surfaces with oil free compressed air to ensure complete removal of all dust and loose particles.

#### Mixing of Nitomortar PE

Mix only the quantity of Nitomortar PE that can be applied within the usable life. Pour a small quantity of the resin into the mixing bucket provided and slowly add the powdered catalyst from the polythene bag and stir until a smooth putty like consistency is obtained. Mix further quantities as required and retain some material for making good after removing the injection nipples.

#### Application of Nitomortar PE

Immediately after mixing, apply the compound to the surface cracks. Overlap the cracks on both sides by 15 - 20mm. In general aim to form a band of 30 -40mm width and 2 - 3 mm thick. Use the material to bond on injection nipples using locating pins to ensure correct sitting. Depending on the width and depth of the cracks the distance between nipples should be 200 to 500mm.

Take care not to block the nipple holes with Nitomortar PE.

Seal the surfaces of the cracks, using Nitomortar PE.

Application of the injection system may be commenced as soon as the Nitomortar PE has cured ( at least 2 hours )

Note : At low ambient temperatures the curing time must be extended in order to allow sufficient strength to build up in the sealant.

# Conbextra® WS60

## Conbextra WS60

Thoroughly mix the accelerator with the base resin. Take care to exclude moisture as much as possible and place in an enclosed container after mixing. There will be a skin on the surface but the liquid underneath will be satisfactory for use.

Conbextra WS60 should be used with standard injection equipment having closed containers.

When flowing water has been stopped, reinject with Conbextra UR63 to give permanent seal. See the datasheet.

## Making good

Remove the nipples. Make good any holes or voids with more sealing compound and allow to cure. The Nitokit surface sealant used to seal cracks can then be ground off, or softened with a blow lamp and peeled off. Do not allow to burn.

## Cleaning

Use Nitoflor Sol

## Storage

Six months shelf life if stored at 20°C

## Packaging

Usually available in 2kg packs

## Precautions

### Health and safety

Some people are sensitive to resins so gloves and a barrier cream should be used when handling Conbextra WS60. If contact with the resin occurs, it must be removed, before it hardens, with a resin removing cream. Follow by washing with soap and water. Do not use solvent. The use of goggles is recommended but should accidental eye contamination occur, wash thoroughly with plenty of water and seek medical treatment immediately. Ensure good ventilation and do not smoke during use.

### Fire

Nitomortar PE and Nitoflor Sol are flammable

### Flash point

Nitoflor Sol 33°C

Nitomortar PE resin 29°C

### Additional information

Conbextra WS60 is part of a wide range of adhesive, grouts, repair mortars and sealing compounds specifically designed and manufactured by Fosroc for the construction industry.

® Denotes the trademark of Fosroc International Limited

### Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

### telephone

++91 80-22240018/120

### fax

++91 80-22233474

### e-mail

india@fosroc.com

### Regional Offices



## Fosroc Chemicals (India) Pvt. Ltd.

### Head Office

111/3, Hafeeza Chamber II Floor,  
K H Road, PBNo. 2744, Bangalore 560027  
[www.fosroc.com](http://www.fosroc.com)

### Bangalore

Shankar House, IV Floor  
1 & 18, RMV Extension  
Bangalore 560 080  
Ph:080-2361 3161/2361 2004  
Fax : 080-2361 7454  
email: Bangalore@fosroc.com

### Mumbai

208/209, Persepolis  
Sector 17, Vashi  
Navi Mumbai 400 703  
Ph:022-2789 6412/14  
Fax: 022 - 2789 6413  
email:Mumbai@fosroc.com

### Delhi

First floor, 1/2 East Patel Nagar  
Opp: Vivek Cinema, Main Patel Rd  
New Delhi 110 008  
Ph:011-25884903/4  
Fax: 011-25884422  
email:Delhi@fosroc.com

### Kolkata

P-569, Lake Terrace Extn.  
First Floor  
Kolkata 700 029  
Ph: 033 24650917 / 55343188  
Fax: 033-24650891  
email:Kolkata@fosroc.com

- Ahmedabad : (079) 26762799 ● Ankleshwar : (02646) 220704/224687 ● Bhubaneswar : (0674) 2546415 ● Chennai (044) 24899949/24853383
- Chandigarh : (0172) 2639360 ● Cochin : (0484) 2356668 ● Coimbatore : (0422) 2472966 ● Goa : (0832) 2542465 ● Guwahati (0361) 2548793
- Hyderabad : (040) 27662324/27662425 ● Hubli (0836) 09343402597 ● Indore : (0731) 504339/5061477 ● Jaipur : (0141) 2235349
- Jamshedpur : (0657) 2223848 ● Lucknow : (0522) 2239044 ● Nagercoil 09842134873 ● Visakhapatnam : (0891) 2564850 / 2707607

INDIA/2005/0323/A

