



Nitoprime® XG

Moisture insensitive epoxy primer for cementitious substrates

Uses

It is suitable for priming concrete surfaces prior to the application of any of the Nitoflor SL2000/4000 and TF range of resin based floor toppings, Nitocote range of protective coatings or Nitomortar epoxy repair mortars.

Advantages

- Can be applied even on damp moist surfaces
- Improves the adhesion of epoxy floor toppings and epoxy mortars with the substrate.

Description

Nitoprime XG is a two component epoxy based primer with good penetrating properties for concrete surfaces.

Technical support

Fosroc provides a countrywide technical advisory service supported by a team of specialists in the field.

Properties

Nitoprime XG	20°C	30°C
Pot life	90 min.	45-50 min.
Temperature limitations	Recommended application range is 10°C - 40°C. Consult local Fosroc office where application is outside the range of 10°C - 40°C.	

Application instructions

Surface preparation

For best results it is recommended to use Nitoprime XG on concrete which is at least 7 days old, and prepared surface as per standard practice.

New concrete floors

Shall be at least 7 days old before proceeding with primer application. Laitance and deposits on new concrete floors are best removed by light grit blasting, mechanical scabbling or grinding. On smaller areas thorough etching using Reebaklens may be considered. After etching the floor, it should be thoroughly washed with clean water.

Old concrete floors

Mechanical cleaning methods as described above are strongly recommended on old concrete floors, particularly where heavy contamination by oil and grease has occurred or existing coatings are present. These may well have been absorbed several millimeters deep into the concrete. To ensure good adhesion all contamination should be removed and the surface thoroughly cleaned of all dust and loose debris. A thorough detergent wash is also recommended followed by thorough cleaning with clean water.

Mixing

The base and hardener contents are to be transferred in to a suitable container and mixed thoroughly for 3 mins. until homogeneous, using a slow speed drill (400 - 500 rpm) fitted with a suitable mixing paddle.

Application

Once mixed the primer should be applied immediately in a thin continuous film to the clean prepared surface. Work the primer into the surface using a stiff brush or roller. Excess application and puddling should be avoided. On porous surfaces Nitoprime XG will be absorbed very quickly leaving characteristic light coloured dry patches. It is recommended that a second priming coat be applied to these dry areas. This not only helps to ensure good adhesion but also prevents air release from the porous substrate which may cause bubbles in the final epoxy topping later.

For Nitoflor SL2000 / 4000 and Nitocote/Nitoflor coatings applications, leave the Nitoprime XG to dry overnight. For Nitoflor TF and Nitomortar, allow Nitoprime XG to become tacky.

Cleaning

All tools and equipments should be cleaned with water immediately after use. Spillages should be absorbed with sand or sawdust and disposed off in accordance with local regulations.

Limitations

Temperature limitations

Recommended application range is 10 °C - 40°C. Consult Fosroc where application or service is outside the range of 10°C to 40°C.

Nitoprime® XG

Estimating

Packaging and coverage

Nitoprime XG is available in 1 litre pack.

Coverage

	Approximate coverage rate
Nitoprime XG	5.2 - 6.2 m ² /litre

The coverage depends on substrate conditions.

Over vacuum dewatered floors finished with power trowels, after surface preparation, coverage of Nitoprime XG may exceed for the above values.

Storage

Nitoprime XG has a shelf life of 6 months when stored in unopened containers under normal warehouse conditions.

Precautions

Health & Safety

Nitoprime XG should not come into contact with skin and eyes or be swallowed. Avoid prolonged inhalation of solvent vapours.

Some people are sensitive to epoxy resins, hardeners and solvents. Gloves, goggles and barrier creams should therefore be used while handling the product. Adequate ventilation should be ensured and if working in enclosed areas, suitable breathing apparatus must be used. If the resin comes in contact with skin, it must be removed before it hardens with a resin removing cream, followed by washing with soap and water - solvent should not be used.

Should accidental eye contamination occur with any of the above products, it should be washed well with plenty of water and medical advice should be sought. If swallowed medical attention should be sought immediately. Vomiting should not be induced.

Fire

Do not expose to naked flames or other sources of ignition. Do not smoke while handling the materials. Containers should be tightly sealed when not in use. In the event of fire, extinguish with CO₂ or foam type extinguishers.

® Denotes the trademark of Fosroc International Limited

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone	fax	e-mail
+91 80-22240018/120	++91 80-22233474	india@fosroc.com

Regional Offices



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

111/3, Hafeeza Chamber II Floor,
K H Road, PBNo. 2744, Bangalore 560027

www.fosroc.com

Bangalore

Shankar House, IV Floor
1 & 18, RMV Extension
Bangalore 560 080
Ph:080-2361 3161/2361 2004
Fax : 080-2361 7454
email: Bangalore@fosroc.com

Mumbai

208/209, Persepolis
Sector 17, Vashi
Navi Mumbai 400 703
Ph:022-2789 6412/14
Fax: 022 - 2789 6413
email:Mumbai@fosroc.com

Delhi

First floor,1/2 East Patel Nagar
Opp: Vivek Cinema, Main Patel Rd
New Delhi 110 008
Ph:011-25884903/4
Fax: 011- 25884422
email:Delhi@fosroc.com

Kolkata

30/B Jodhpur Park
Ground Floor
Kolkata 700 068
Ph: 033 2472 5482
Fax: 033-2472 9921
email:Kolkata@fosroc.com

●Ahmedabad : (079) 26762799 ●Ankleshwar : (02646) 220704/224687 ●Bhubaneshwar : (0674) 2521176 ● Chennai (044) 24899949/24853383
●Chandigarh : (0172) 2639360 ● Cochin : (0484) 2356668 ●Coimbatore : (0422) 2472966 ●Goa : (0832) 2542465 ●Guwahati (0361) 2548793
●Hyderabad : (040) 27662324/27662425 ● Hubli (0836) 3402597 ●Indore : (0731) 504339/5061477 ● Jaipur : (0141) 2235349 ● Lucknow : (0522) 22239044 ● Nagercoil (04652) 2224849 ● Mangalore: (0824) 22272234 ● Visakhapatnam : (0891) 2564850

INDIA/2004/0504/B

