



Nitocote® EPW100

Water dispersed epoxy coating and sealer

Uses

Nitocote EPW100 coating provides a pigmented sealing coat onto cementitious and concrete surfaces providing dustproof, easily cleanable and resistant to penetration of oils and liquids. The cured film is resistant to corrosion, chemicals and abrasion. Suitable for application to reservoirs, tanks, ducts, silos, water treatment works, breweries, dairies, kitchens and food processing plants. The cured film forms a waterproof barrier and is non-toxic.

Also recommended as internal waterproof coating.

Advantages

- **Improves** the resistance of concrete to many industrial chemicals.
- **Hygienic** - easily cleaned due to impervious finish.
- **Odour free** - environmental friendly.
- **Water based** - all tools and equipment can be cleaned with water.
- **Economic** and easy to apply.
- **Attractive** - available in a range of colours.
- **Antifungal** - resistant to fungal attack.

Description

Nitocote EPW100 is a three component prepacked, water dispersed epoxy resin system supplied ready for onsite mixing and use.

The cured film forms a hard, flexible, matt seal to concrete and other substrates.

Technical support

Fosroc offers technical support service to specifiers, end users and contractors, as well as onsite technical assistance in locations all over the country.

Properties

	@20°C	@30°C
Usable life	2 hrs	1 hr
Time between coats	Within 24 hrs	Within 16 hrs
Initial hardness	30 hrs	24 hrs
Full cure	21 days	21 days

Note : After the usable life has expired, the material although not hardened, increases in viscosity and the characteristics of the product change. Excess material should be discarded after this point.

Chemical resistance

Samples of Nitocote EPW100 coating have been subjected to constant immersion at 30°C for 3 months in the following chemicals and have been found to be unaffected.

- Dilute Sulphuric acid
- Dilute Citric acid
- Dilute Sodium Hydroxide
- Ammonia 10% solution
- Oil and grease
- Petrol
- Tap water

Good housekeeping is essential in areas where chemical spillage is likely to occur. It is especially important that such spillage should not be allowed to dry as higher concentrations of chemicals are involved.

Where chemicals at higher temperatures are involved, Fosroc shall be contacted.

Application instructions

Preparation

Surfaces to be treated should be clean and free from all contamination. Oil or grease should be removed by suitable means, followed by washing off with clean water. Excess laitence should be removed by etching with Reebaklens followed by washing off with clean water.

Mixing

The paste component of Nitocote EPW100 coating system shall be added to the hardener component and then stirred for a period of 3 minutes followed by addition of base. The resultant mix is further mixed for a period of 2 - 3 minutes. The use of a slow speed drill fitted with a paddle is recommended.

Coating

The mixed Nitocote EPW100 coating shall be applied to the prepared and cleaned surface, using a brush or lambswool roller. ensuring that the area is completely coated and that 'ponding' of the material does not occur as water may be trapped and the material will not cure completely.

Nitocote® EPW100

The second coat may be applied as soon as the first coat has initially dried. The time will be dependant on the type of surface and ambient conditions but will be in the range of 24 hours at 30°C.

Temperature limitations

Minimum application temperature is 20°C.

Estimating

Packaging and coverage

Nitocote EPW100 is supplied in 4 litre packs.

The coverage of Nitocote EPW100 coating depends to a large extent on the substrate and site conditions. For calculation purpose 20 - 22m² /pack /per coat @ 180 microns WFT (100 microns DFT) can be taken as the coverage.

Storage

Nitocote EPW100 coating should be stored under normal warehouse conditions, and must be protected from frost.

Shelf life

6 months in unopened containers.

Precautions

Health & Safety instructions

Since some people are sensitive to epoxy resins, gloves, goggles and barrier creams should be used when handling these products. If contact with skin occurs, it must be removed, before it hardens, with resin removing creams followed by washing with soap and water. Solvent should not be used. The use of goggles is recommended but should accidental eye contamination occur, washing thoroughly with plenty of water and seeking immediate medical treatment is suggested.

Fire

Nitocote EPW100 coating is non-flammable.

Additional information

Fosroc manufactures a wide range of products specifically designed for the repair and refurbishment of damaged reinforced concrete. This includes repair mortars, fluid micro concretes, chemical resistant epoxy mortars in addition to comprehensive package of protective coatings. In addition, a wide range of complementary products are available. This includes admixtures, joint sealants, waterproofing membranes, grouts and anchors specialised flooring materials and bonding agents.

Separate data sheets are available on these products

® Denotes the trademark of Fosroc International Limited

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone

++91 80-22240018/120

fax

++91 80-22233474

e-mail

india@fosroc.com



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

111/3, Hafeeza Chamber II Floor,
K H Road, PBNo. 2744, Bangalore 560027
www.fosroc.com

Regional Offices

Bangalore

Shankar House, IV Floor
1 & 18, RMV Extension
Bangalore 560 080
Ph:080-2361 3161/2361 2004
Fax : 080-2361 7454
email: Bangalore@fosroc.com

Mumbai

208/209, Persepolis
Sector 17, Vashi
Navi Mumbai 400 703
Ph:022-2789 6412/14
Fax: 022 - 2789 6413
email:Mumbai@fosroc.com

Delhi

First floor,1/2 East Patel Nagar
Opp: Vivek Cinema, Main Patel Rd
New Delhi 110 008
Ph:011-25884903/4
Fax: 011- 25884422
email:Delhi@fosroc.com

Kolkata

30/B Jodhpur Park
Ground Floor
Kolkata 700 068
Ph: 033 2472 5482
Fax: 033-2472 9921
email:Kolkata@fosroc.com

●Ahmedabad : (079) 26762799 ●Ankleshwar : (02646) 220704/224687 ●Bhubaneshwar : (0674) 2521176 ● Chennai (044) 24899949/24853383
●Chandigarh : (0172) 2639360 ● Cochin : (0484) 2356668 ●Coimbatore : (0422) 2472966 ●Goa : (0832) 2542465 ●Guwahati (0361) 2548793
●Hyderabad : (040) 27662324/27662425 ● Hubli (0836) 3402597 ●Indore : (0731) 504339/5061477 ● Jaipur : (0141) 2235349 ● Lucknow : (0522)
22239044 ● Nagercoil (04652) 2224849 ● Mangalore: (0824) 22272234 ● Visakhapatnam : (0891) 2564850

INDIA/2004/0652/D

